

**Kiwa GmbH**

TBU

Gutenbergstraße 29

D-48268 Greven

Kiwa GmbH - TBU, Gutenbergstraße 29, D-48268 Greven

BPA GmbH  
 Behringstrasse 12  
 71083 Herrenberg-Gültstein  
 GERMANY

T: +49 (0) 2571 9872 - 0  
 F: +49 (0) 2571 9872 - 99  
 E: [infokiwagreven@kiwa.de](mailto:infokiwagreven@kiwa.de)

[www.kiwa.de](http://www.kiwa.de)

## Summary of results

Date / Ref. : 04 February 2019 / mk

Material : PVC sealing membrane (transparent) with one sided PP nonwoven (white)  
**DualProof T series**

Test	Standard	Unit	Result
<b>Adhesives for tiles -Determination of tensile adhesion strength for cementitious adhesives</b>  Test after 7 days storage at 23°C Test after 28 days storage at 23°C Test after 28 days storage at 50°C	<b>in accordance to 11.2007                      DIN EN 1348</b>	N/mm <sup>2</sup> N/mm <sup>2</sup> N/mm <sup>2</sup>	0,515 0,626 0,679
<b>Testing hardened concrete -                      Part 8: Depth of penetration of water under pressure</b>  Water-pressure test up to 5 bar over a time period of 28 days with a puncture damage in the membrane with a diameter of 2 cm.	<b>in accordance to 07.2009                      DIN EN 12390-8</b>		No lateral waterflow

*i.V. Matthias Käsekamp*  
 i.V. Matthias Käsekamp, B. Eng.  
 (Head of test laboratory)


